



TigerTurf™
ENDURANCE+




Adding texturized monofilament thatch to durable XPS slit film fibers provides robust, durable playing surface performance.

The thatch layer provides additional support to help mitigate infill migration and instability when used with lightweight infills. XPS fibers are the most durable in the world, so teams will have a great playing surface for years to come.

TURF

PILE CONTENT



BLEND OF DURABLE SLIT FILM AND TEXTURIZED MONOFILAMENT FIBERS

TenCate XPS Plus slit film, U.V. resistant, combined with TenCate TXT monofilament root zone

PRIMARY BACKING

7.5 oz/yd²; TenCate K29 Backing (Double Layer Thiobac, black, U.V. stabilized; Layer 1: 100% PP, Layer 2: PET/PP blend)

SECONDARY BACKING

20 oz/yd² Polyurethane coating with drainage holes

TOTAL WEIGHT

83.5 oz/yd²

PILE HEIGHT

1 5/8 inch

FACE WEIGHT*

56 oz/yd²

MACHINE GAUGE

1/2 inch

SET UP

2 ends/needle

ROLL WIDTH

182 inch

WATER PERMEABILITY

> 50 inches/hour

TUFT BIND (ASTM D1335)

≥ 8 lbs

GRAB TEAR (ASTM D5034)

250/250 lbs

PILL FLAMMABILITY (ASTM D2859)

Pass



BEST FOR BASEBALL, SOFTBALL, INDOOR AND MULTI-PURPOSE FIELDS

MADE IN THE USA

TENCATE GRASS

WHEN USED WITH LIGHTWEIGHT INFILLS

Pile Height, Max Thickness, Face Weight, Primary & Secondary Backing, and Total Weight can differ by ±10%. The Stitch Rate will change according to the exact specifications and can differ by ±1. Roll Width can differ by ±0.8 inch.

TenCate Grass has the right to alter each product specification in order to improve the system according to the latest standards. TenCate Grass is not legally liable in case of noncompliance with the above mentioned specifications.

*Face Weight reflects entire length of yarn, including portion woven into backing, which is consistent with standard ASTM method of measuring tuft including back stitch.

**For details on thatch color, refer to the Standard Color Sheet.

YARN

DENSITY (DENIER)

10,000/1 (XPS);
5,000/8 (thatch)

THICKNESS (MICRONS)

120 (XPS); 100 (thatch)

MELTING POINT

128° C | 260° F

BREAKING STRENGTH

24 lbs/force (XPS);
17 lbs/force (thatch)

LEAD CONTENT (PPM)

<100

STANDARD COLORS**



FIELD GREEN
Pantone: 575C



LIME GREEN
Pantone: 7496C



FIELD GREEN/
LIME GREEN



BROWN
Pantone: 1545C



NAVY BLUE
Pantone: 282C



FLORIDA BLUE
Pantone: 281C



GRAY
Pantone: 422+429



BLACK
Pantone: 000C



RED
Pantone: 185C



ORANGE
Pantone: 166C



BLUE LAGOON
Pantone: 2925C



RED CLAY
Pantone: 7526C



CRIMSON
Pantone: 202C



BLUEPLE
Pantone: 268C



TAN
Pantone: 728C



BRIGHT YELLOW
Pantone: 136C



WHITE
Pantone: 000



VEGAS GOLD
Pantone: 466C